

SPECIFICATION SHEET

CROSSWORD

CONSTRUCTION	VLOC
PILE FIBER COMPOSITION	100% Nylon (Polyamide6)
YARN TYPE	Frieze
DYE METHOD	Solution Dyed
PILE WEIGHT	710g/m2
NUMBER OF TUFTS	260150/m2
TUFTING GAUGE	1/12"
PRIMARY BACKING	Non-Woven
BACKING STRUCTURES	StableShield 100% Vinyl
OPTIONAL BACKING	Recova 500 & Recova 800
TILE SIZE	50x50cm
PILE HEIGHT	3.5mm
TOTAL HEIGHT	6.5mm
PILE TREATMENT	UV Treated Yarn, Walk Of Fame (Optional)
RECOMMENDED	Quarter Turn or Brick



PERFORMANCE SPECIFICATION

WEAR CLASSIFICATION	HEAVY CONTRACT	
VOC EMISSION	ASTM D5116-17	<0.5 mg/m²/hour (CRI GLP)
FLAMMABILITY	ASTM D-2859//FF 1-70//16CFR 1630	Pass 8/8
REACTION TO FIRE	EN ISO 9239-1 (2010)	Cfl-s1
STATIC PROPENSITY	AATCC 134-2011	0.2 kV
COLOR FASTNESS	AATCC/16	5/5 on Grey Scale
THERMAL RESISTANCE	DIN 52612	.04m2 K/W
IMPACT SOUND INSULATION	ISO 140-8	ΔLw 23dB
SOUND ABSORPTION LEVEL	EN ISO 354	aw: 0.15(H)
SOILING PROPENSITY	ASTM D 6540-00	4
DIMENSIONAL STABILITY	EN 986	< 0.20%
CASTOR CHAIR TEST	ISO 4918	Rating 4.0



































Color may slightly vary from one dye lot to another dye lot

Total weight of the product can have a normal variation of ± 5%

We reserve the right to amend the above specification without prior notice with changes in raw material supplies

