

SPECIFICATION SHEET

MAINCREEK

CONSTRUCTION	LOOP
PILE FIBER COMPOSITION	100% Nylon (Polyamide 6)
YARN TYPE	BCF
DYE METHOD	Solution Dyed
PILE WEIGHT	630g/m2
NUMBER OF TUFTS	209350/m2
TUFTING GAUGE	1/10"
PRIMARY BACKING	Non-Woven
SECONDARY BACKING	Stable Shield - 100% Vinyl
OPTIONAL BACKINGS	Recova-PU Cushion , EcoShield-100% Recycled Vinyl
TILE SIZE	50 cm x 50 cm
PILE HEIGHT	3.5 mm / 5.0 mm
TOTAL HEIGHT	7.0 mm
PILE TREATMENT	INVISTA Anti-Soil Treatment, Anti-Microbial (optional)
RECOMMENDED	Quarter Turn or Brick

PERFORMANCE SPECIFICATION

WEAR CLASSIFICATION He	leavy Contract	
VOC EMMISION AS	STM D5116-06	<0.5 mg/m²/hour
FLAMMABILITY AS	STM D-2859//FF 1-70//16CFR 1630 F	Pass 8/8
CRITICAL RADIANT FLUX AS	STM E648-08	Class 1
STATIC PROPENSITY IS	5O 6356	0.2 kV
COLOUR FASTNESS AA	ATCC/16	5/5 on Grey Scale
THERMAL RESISTANCE IS	5O 8302	.04m²K/W
IMPACT SOUND INSULATION IS	SO 140-8	ΔLw 23dB
SOUND ABSORPTION LEVEL EN	N ISO 11654	aw: 0.15(H)
SOILING PROPENSITY AS	STM D 6540-00	4
DIMENSIONAL STABILITY EN	N 986	< 0.20%
CASTOR CHAIR TEST DI	IN 54324	R≥2.4
SMOKE DENSITY EN	N ISO 9239-1:2002	< 450




































• Total weight of the product can have a normal variation of ± 5%

We reserve the right to amend the above specification without prior notice with changes in raw material supplies

