

SPECIFICATION SHEET

LAST CHANCE

CONSTRUCTION	LOOP
PILE FIBER COMPOSITION	100% Olefin
YARN TYPE	BCF
DYE METHOD	Solution Dyed
PILE WEIGHT	650g/m2
NUMBER OF TUFTS	184860/m2
TUFTING GAUGE	1/12"
PRIMARY BACKING	Non-Woven
BACKING STRUCTURES	StableShield 100% Vinyl
TILE SIZE	50x50cm
PILE HEIGHT	2.3mm / 5.5mm
TOTAL HEIGHT	8.0mm
PILE TREATMENT	INVISTA Anti-Soil Treatment, Anti Microbial (optional)
RECOMMENDED	Quarter Turn or Brick

PERFORMANCE SPECIFICATION

VOC EMISSION	ASTM D5116-06	<0.5 mg/m²/hour (CRI GLP)
FLAMMABILITY	ASTM D-2859//FF 1-70//16CFR 1630	Pass 8/8
REACTION TO FIRE	EN ISO 9239-1:2002	Dfl-s1
STATIC PROPENSITY	ISO 6356	0.2 kV
COLOR FASTNESS	AATCC/16	5/5 on Grey Scale
THERMAL RESISTANCE	ISO 8302	.04m2 K/W
IMPACT SOUND INSULATION	ISO 140-8	ΔLw 23dB
SOUND ABSORPTION LEVEL	EN ISO 11654	aw: 0.15(H)
SOILING PROPENSITY	ASTM D 6540-00	4
DIMENSIONAL STABILITY	EN 986	< 0.20%
CASTOR CHAIR TEST	DIN 54324	R ≥ 2.4































Color may slightly vary from one dye lot to another dye lot

Total weight of the product can have a normal variation of ± 5%



We reserve the right to amend the above specification without prior notice with changes in raw material supplies