




SPECIFICATION SHEET

DUECE

| | |
|--------------------------|--|
| CONSTRUCTION | LOOP PILE TIP SHEARED |
| PILE FIBER COMPOSITION | 100% Olefin |
| YARN TYPE | BCF |
| DYE METHOD | Solution Dyed |
| PILE WEIGHT | 850 g/m ² |
| NUMBER OF TUFTS | 194340/m ² |
| TUFTING GAUGE | 1/12" |
| PRIMARY BACKING | Non-Woven |
| SECONDARY BACKING | StableShield- 100% Vinyl |
| OPTIONAL BACKINGS | Recova-PU Cushion, EcoShield-100% Recycled Vinyl |
| TILE SIZE | 50 cm x 50 cm (19.6 in x 19.6 in) |
| PILE HEIGHT | 3.0 mm / 5.00 mm |
| TOTAL HEIGHT | 7.5 mm |
| PILE TREATMENT | INVISTA Anti-Soil Treatment, Anti-Microbial (Optional) |
| RECOMMENDED INSTALLATION | Quarter Turn or Brick |

PERFORMANCE SPECIFICATION

| | | |
|-------------------------|----------------------------------|--|
| WEAR CLASSIFICATION | HEAVY CONTRACT | |
| VOC EMISSION | ASTM D5116-06 | <0.5 mg/m ² /hour (CRI GLP) |
| FLAMMABILITY | ASTM D-2859//FF 1-70//16CFR 1630 | Pass 8/8 |
| CRITICAL RADIANT FLUX | ASTM E648-08 | Class 1 |
| STATIC PROPENSITY | ISO 6356 | 0.2 kV |
| COLOR FASTNESS | AATCC/16 | 5/5 on Grey Scale |
| THERMAL RESISTANCE | ISO 8302 | .04m ² K/W |
| IMPACT SOUND INSULATION | ISO 140-8 | ΔLw 23dB |
| SOUND ABSORPTION LEVEL | EN ISO 11654 | αw: 0.15(H) |
| SOILING PROPENSITY | ASTM D 6540-00 | 4 |
| DIMENSIONAL STABILITY | EN 986 | < 0.20% |
| CASTOR CHAIR TEST | DIN 54324 | R ≥ 2.4 |
| SMOKE DENSITY | EN ISO 9239-1:2002 | <450 |



- Shading or Pile reversal is nature of cut pile carpet and it is not manufacturing defect
- Color may slightly vary from one dye lot to another dye lot
- Total weight of the product can have a normal variation of ± 5%
- We reserve to amend the above specification without prior notice due variables in raw material supplies

